SOD

$Im\bar{3}m$

Framework Type Data



framework viewed along [100]

Idealized cell data: cubic, $Im\bar{3}m$, $a = 9.0$Å

Coordination sequences and vertex symbols:

T_1 (12, $\bar{4}2m$)	4	10	20	34	52	74	100	130	164	202	4·4·6·6·6·6

Secondary building units: 6

Framework description: ABC sequence of 6-rings

Composite building units: *sod*



Materials with this framework type:

*Sodalite[1,2]
[Al-Co-P-O]-**SOD**[3]
[Al-Ga-Si-Ge-O]-**SOD**[4]
[Al-Ge-O]-**SOD**[5,6]
[Be-Al-Si-O]-**SOD**[7]
[Be-As-O]-**SOD**[8]
[Be-Ge-O]-**SOD**[9]
[Be-P-O]-**SOD**[8]
[Be-Si-O]-**SOD**[9,10]
[Co-Ga-P-O]-**SOD**[3,11]
[Ga-Ge-O]-**SOD**[6]
[Ga-Si-O]-**SOD**[12]
[Zn-Al-As-O]-**SOD**[13]
[Zn-As-O]-**SOD**[14]
[Zn-Ga-As-O]-**SOD**[11,13]
[Zn-Ga-P-O]-**SOD**[11]
[Zn-P-O]-**SOD**[14]
[Zn-Si-O]-**SOD**[15]
$|Ca_8(WO_4)_2|[Al_{12}O_{24}]$-**SOD**[16]
AlPO-20 plus variants[17,18]
Basic sodalite[19,20]
Bicchulite[21]
Danalite[22]
G[23]
Genthelvite[24]
Hauyn[25]
Helvin[22]
Hydroxo sodalite[26]
Nosean[27]
SIZ-9[28]
Silica sodalite[29]
TMA sodalite[30]
Tugtupite[31,32]

Type Material: Sodalite — SOD

Type Material Data

Crystal chemical data: $|Na_8Cl_2|[Al_6Si_6O_{24}]$-**SOD**
cubic, $P\bar{4}3n$, a = 8.870Å [2]

Framework density: 17.2 T/1000Å^3

Channels: apertures formed by 6-rings only

References:

(1) Pauling, L. *Z. Kristallogr.*, **74**, 213-225 (1930)
(2) Loens, J. and Schulz, H. *Acta Crystallogr.*, **23**, 434-436 (1967)
(3) Feng, P., Bu, X. and Stucky, G.D. *Nature*, **388**, 735-741 (1997)
(4) Johnson, G.M., Mead, P.J. and Weller, M.T. *Microporous Mesoporous Mat.*, **38**, 445-460 (2000)
(5) Wiebcke, M., Sieger, P., Felsche, J., Engelhardt, G., Behrens, P. and Schefer, J. *Z. anorg. allg. Chemie*, **619**, 1321-1329 (1993)
(6) Bu, X., Feng, P., Gier, T.E., Zhao, D. and Stucky, G.D. *J. Am. Chem. Soc.*, **120**, 13389-13397 (1998)
(7) Armstrong, J.A. and Weller, M.T. *J. Chem. Soc., Dalton Trans.*, 2998-3005 (2006)
(8) Gier, T.E., Harrison, W.T.A. and Stucky, G.D. *Angew. Chem., Int. Ed.*, **30**, 1169-1171 (1991)
(9) Dann, S.E., Weller, M.T., Rainford, B.D. and Adroja, D.T. *Inorg. Chem.*, **36**, 5278-5283 (1997)
(10) Dann, S.E. and Weller, M.T. *Inorg. Chem.*, **35**, 555-558 (1996)
(11) Bu, X., Gier, T.E., Feng, P. and Stucky, G.D. *Microporous Mesoporous Mat.*, **20**, 371-379 (1998)
(12) McCusker, L.B., Meier, W.M., Suzuki, K. and Shin, S. *Zeolites*, **6**, 388-391 (1986)
(13) Feng, P., Zhang, T. and Bu, X. *J. Am. Chem. Soc.*, **123**, 8608-8609 (2001)
(14) Nenoff, T.M., Harrison, W.T.A., Gier, T.E. and Stucky, G.D. *J. Am. Chem. Soc.*, **113**, 378-379 (1991)
(15) Camblor, M.A., Lobo, R.F., Koller, H. and Davis, M.E. *Chem. Mater.*, **6**, 2193-2199 (1994)
(16) Depmeier, W. *Acta Crystallogr.*, **C40**, 226-231 (1984)
(17) Wilson, S.T., Lok, B.M., Messina, C.A., Cannan, T.R. and Flanigen, E.M. *J. Am. Chem. Soc.*, **104**, 1146-1147 (1982)
(18) Flanigen, E.M., Lok, B.M., Patton, R.L. and Wilson, S.T. *Proc. 7th Int. Zeolite Conf.*, pp. 103-112 (1986)
(19) Barrer, R.M. and White, E.A.D. *J. Chem. Soc.*, 1267-1278 (1951)
(20) Hassan, I. and Grundy, H.D. *Acta Crystallogr.*, **C39**, 3-5 (1983)
(21) Sahl, K. and Chatterjee, N.D. *Z. Kristallogr.*, **146**, 35-41 (1977)
(22) Glass, J.J., Jahns, R.H. and Stevens, R.E. *Am. Mineral.*, **29**, 163-191 (1944)
(23) Shishakova, T.N. and Dubinin, M.M. *Izv. Akad. Nauk SSSR*, 1303- (1965)
(24) Merlino, S. *Feldspars and Feldspathoids*, pp. 435-470 (1983)
(25) Loehn, J. and Schulz, H. *N. Jb. Miner. Abh.*, **109**, 201-210 (1968)
(26) Felsche, J., Luger, S. and Baerlocher, Ch. *Zeolites*, **6**, 367-372 (1986)
(27) Schulz, H. and Saalfeld, H. *Tschermaks Min. Petr. Mitt.*, **10**, 225-232 (1965)
(28) Parnham, E.R. and Morris, R.E. *J. Am. Chem. Soc.*, **128**, 2204-2205 (2006)
(29) Bibby, D.M. and Dale, M.P. *Nature*, **317**, 157-158 (1985)
(30) Baerlocher, Ch. and Meier, W.M. *Helv. Chim. Acta*, **52**, 1853-1860 (1969)
(31) Sorensen, H. *Am. Mineral.*, **48**, 1178 (1963)
(32) Hassan, I. and Grundy, H.D. *Can. Mineral.*, **29**, 385-390 (1991)